

## CREMONE® 产品数据表



### Butyl Reclaimed Rubber

Item	Unit	Specification	Test Method
Acetone Extract	%	8 ± 4	ISO1407
Ash Content	%	6 ± 3	ASTM D6370-99
Carbon Black	%	30 ± 5	ASTM D6370-99
Rubber Hydrocarbon	%	> 50	ASTM D6370-99
Specific Gravity	g/cm <sup>3</sup>	1.17 ± 0.03	ASTM D297
Mooney Viscosity ML (1 + 4) @100°C	MU	40 ± 10	ASTM D1646
Hardness	Shore A	50 ± 5	ASTM D2240
Tensile Strength	MPA	>8.0	ASTM D412
Elongation At Break	%	> 460	ASTM D412

### PACKING

Per bale size	56cm*32cm*10cm
Per bale weight	20kg
Container size	20feet
Net weight	26,200kg

### STORAGE

- Store in a cool, dry, well ventilated place to avoid direct sunlight.

CREMONE CHEMICALS CO., LTD.

Add: Room 1106, 1168 HUYI Road, Jiading District, Shanghai, China

Tel: +86-021-58626709

Email: [service@cremonechem.com](mailto:service@cremonechem.com)