

CREMONE® 产品数据表



Natural Reclaimed Rubber

Item	Unit	Specification	Test Method
Acetone Extract	%	18 ± 5	ISO1407
Ash Content	%	5 ± 3	ASTM D6370-99
Carbon Black	%	30 ± 5	ASTM D6370-99
Rubber Hydrocarbon	%	55 ± 5	ASTM D6370-99
Specific Gravity	g/cm ³	1.15 ± 0.03	ASTM D297
Mooney Viscosity ML (1 + 4) @100°C	MU	55 ± 10	ASTM D1646
Hardness	Shore A	60 ± 5	ASTM D2240
Tensile Strength	MPA	>9	ASTM D412
Elongation At Break	%	>280	ASTM D412

PACKING

Per bale size	66cm*44cm*8cm
Per bale weight	20kg
Container size	20feet
Net weight	25,000kg

STORAGE

- Store in a cool, dry, well ventilated place to avoid direct sunlight.

CREMONE CHEMICALS CO., LTD.

Add: Room 1106, 1168 HUYI Road, Jiading District, Shanghai, China

Tel: +86-021-58626709

Email: service@cremonechem.com