CREMONE °产品数据表



Zinc Oxide

| Item | Unit | Indirect Method Zinc Oxide | Active Zinc Oxide | Test Method |
|---------------------------|-------|-------------------------------|------------------------------|------------------------|
| Appearance | 1 | White powder | White or light yellow powder | er / |
| Zinc oxide content | % | ≥99.5 | ≥95.0 | GB/T 11409 |
| Cd | % | ≤0.01 | ≤0.01 | ICP |
| Pd | % | ≤0.05 | ≤0.03 | ICP |
| Mn | % | ≤0.0003 | ≤0.0005 | ICP |
| Cu | % | ≤0.0007 | ≤0.003 | ICP |
| Loss on ignition | % | ≤0.4 | ≤4.0 M | luffle furnace 850℃/2H |
| Hydrochloric acid insolub | les / | ≤0.03 | ≤0.05 | GB/T 3185 |

PRODUCT FEATURE

- 1 Both are high-purity white powders with excellent chemical stability and transparency.
- ② Indirect method zinc oxide is suitable for high-precision applications in pharmaceuticals and personal care products, offering environmental friendliness and stability.
- 3 Active zinc oxide has higher chemical activity, good dispersibility, corrosion resistance and antibacterial properties.

APPLICATION

Widely used in coatings and paints, rubber products, plastics and resins, pharmaceuticals and personal care, ceramics and glass.

PACKING

- 1 25 kg/bag
- 2 Store in a sealed container in a cool, dry, and well-ventilated place, away from direct sunlight.

CREMONE CHEMICALS CO., LTD.

Add: Room 1106, 1168 HUYI Road, Jiading District, Shanghai, China

Tel: +86-021-58626709 Email: service@cremonechem.com